
## **Refine Search**

#### Search Results -

Term	Documents
525/199	733
525/199S	0
525/200	284
525/200S	0
(((525/200   525/199).CCLS.) AND 2).USPT,EPAB,JPAB,DWPI,TDBD.	48
(525/199-200.CCLS. AND L2 ).USPT,EPAB,JPAB,DWPI,TDBD.	48

US Pre-Grant Publication Full-Text Database
US Patents Full-Text Database
US OCR Full-Text Database
EPO Abstracts Database
JPO Abstracts Database
Derwent World Patents Index
IBM Technical Disclosure Bulletins

Search:



### **Search History**

DATE: Friday, October 29, 2004 Printable Copy Create Case

Set Name side by side	Query	Hit Count	Set Name result set
DB =	USPT,EPAB,JPAB,DWPI,TDBD; PLUR=YES; OP=ADJ		
<u>L1</u>	(particle or particulate or particulated or powder or powdered or powdery or granulate or granulated or grain or pulverulent or spherulite) with (fluorine or fluoride or fluoro)	24925	, <u>L1</u>
<u>L2</u>	(elastomer or elastomeric or rubber or rubbery) and L1	4291	L2
<u>L3</u>	525/199-200.ccls. and L2	48	13

## END OF SEARCH HISTORY


## **Refine Search**

#### Search Results -

Term	Documents
EMULSION	293641
EMULSIONS	112236
(2 AND EMULSION).USPT,EPAB,JPAB,DWPI,TDBD.	57
(EMULSION AND L2 ).USPT,EPAB,JPAB,DWPI,TDBD.	57

US Pre-Grant Publication Full-Text Database
US Patents Full-Text Database
US OCR Full-Text Database
EPO Abstracts Database
JPO Abstracts Database
Derwent World Patents Index
IBM Technical Disclosure Bulletins

Search:



### Search History

DATE: Friday, October 29, 2004 Printable Copy Create Case

Set Name side by side	Query	<u>Hit</u> Count	Set Name result set
DB=U	USPT,EPAB,JPAB,DWPI,TDBD; PLUR=YES; OP=ADJ		
<u>L1</u>	525/199-200.ccls.	856	L1
<u>L2</u>	(transparent or see through or optically clear or light transmissive or translucent or light transmission) and L1	141	<u>L2</u>
<u>L3</u>	emulsion and L2	57	L3

**END OF SEARCH HISTORY** 

Name side by side	Query	<u>Hit</u> <u>Count</u>	Name result set
DB =	USPT,EPAB,JPAB,DWPI,TDBD; PLUR=YES; OP=ADJ		
<u>L1</u>	irie-sadashige\$.in. or mimura-kazuyoshi\$.in. or nishibayashi-hirofumi\$.in. or tanaka-hiroyuki\$.in. or noguchi-tsuyoshi\$.in. or kishine-mitsuru\$.in.	2680	<u>L1</u>
<u>L2</u> .	(elastomer or elastomeric or rubber or rubbery) and L1	188	L2
<u>L3</u>	(fluorine or fluoro\$) and L2	95	<u>L3</u>

# END OF SEARCH HISTORY